1	Scalable synthesis of smooth PS@TiO $_2$ core-shell and TiO $_2$ hollow
2	spheres in the (sub) micron size range: understanding synthesis and
3	calcination parameters
4	
5	Anna M. Lechner, ¹ Tanja Feller, ¹ Qimeng Song ¹ , Bernd A. F. Kopera, ¹ Lukas Heindl, ¹ Markus Drechsler, ²
6	Sabine Rosenfeldt, ¹ Markus Retsch ^{*,1,2}
7	¹ Physical Chemistry I. University of Bayreuth. Universitätsstraße 30. 95440 Bayreuth. Germany.
8	markus retsch@uni-bavreuth.de
0	markasiretsen@am sayreatmae
9 10	² Bavarian Polymer Institute (BPI), University of Bayreuth, Universitätsstraße 30, 95440 Bayreuth, Germany
11 12	KEYWORDS: titania hollow spheres, dispersion polymerization, calcination parameters, panoparticles
12	thermal decomposition
15	
14	
15	ABSTRACT
16	
17	Hollow spheres made from titanium diaxide (TiO_{1}) are interesting structures because of their high
10	surface area and low density combined with comic enducting properties of the TiQ. However, the
10	surface area and low density, combined with semiconducting properties of the HO_2 . However, the
19	synthesis is still challenging because of the high reactivity of the titania precursors. Here, we present a
20	simple, reproducible, and scalable way to synthesize IiO ₂ hollow spheres in the micrometer/sub-
21	micrometer size range comprising three steps: Synthesis of polystyrene template particles, growth of
22	TiO_2 shells, and calcination to hollow spheres. We investigate the importance of adjusting the seed
23	particle surface functionalization via the appropriate choice of co-monomer during the dispersion
24	polymerization. An aging step and a calcination process at low temperatures are mandatory to retain
25	the particle integrity during the seed particle removal. We provide a detailed characterization of each
26	step of this process including electron microscopy, small angle X-ray scattering, simultaneous thermal
27	analysis.

29

30 INTRODUCTION

31 Environmental pollution is worldwide a pressing issue, which needs to be addressed by society, 32 politicians, and researchers. Whereas "chemistry" certainly contributes in various ways to 33 environmental pollution, it also offers solutions towards a more sustainable future. The awareness of 34 this fact led to the field of "green chemistry". It was introduced in 1998 by Paul Anastas and John 35 Warner and is based on twelve principles to design chemical products and processes in an environmental friendly way. [1-3] It includes less hazardous chemical synthesis and solvents, design 36 37 for energy efficiency, and catalysis. One particular materials class that is regularly discussed in the 38 context of green chemistry is titanium dioxide. Titanium dioxide (TiO₂) can be classified as a green 39 chemical or material because of its photocatalytic activity, [4,5] usage in solar cells, [6-8] and batteries, 40 [9-11], low toxicity, and high chemical stability.

TiO₂ exists in many different polymorphs, with rutile, brookite, and anatase being the most prominent ones. The main difference of the three polymorphs is their thermodynamic stability. Rutile is the most stable phase in bulk materials and at high temperatures. [12,13] However, anatase and brookite phases are preferentially formed in small structures in nature as well as during solution-based synthesis. [13-15] An amorphous TiO₂ phase is also known and typically used as the starting material for transformations into phase pure anatase particles at high temperatures > 100 °C. [13,16,17]

In addition to the microscopic structure, the mesoscopic shape of the TiO₂ material is important for photovoltaic, or photonic applications. Different shapes have been tested as electrodes for photovoltaic applications: Thin films, nanoparticle assemblies, inverse opals, and nanotube arrays. [18-23] Nanotube arrays achieved photoconversion efficiencies up to 4.9 % in solar cells, [22], and can also be used for hydrogen storage applications. [24] For optical and photonic applications, typically inverse opal structures are used. [12,25-27] Here, the high refractive index of the different polymorphs of TiO₂ is used in the context of structural coloration or efficient scattering.

54 The different shapes can be achieved via a wide range of synthesis routes. [12,28] The most common 55 and easy one is the sol-gel method, where a precursor is first hydrolyzed in an acidic or basic 56 environment, followed by polymerization into TiO₂. Organic metal compounds or inorganic metal salts 57 are used as precursors. The sol-gel synthesis method leads to a wide variety of structures, from nanoparticles in different sizes shapes to rod- and tube-like structures. Further methods are 58 59 hydrothermal or solvothermal synthesis, where the reaction takes place at temperatures above the 60 boiling point of the solvent up to 240 °C in an autoclave, and thus at high pressures. [12,13,29] Using 61 this method it is possible to generate phase pure nanoparticles or nanorods. Chemical or physical 62 vapor deposition processes are further synthesis methods that lead to oriented nanowire arrays. 63 [12,28]

64 It is also possible to build TiO_2 structures in a templated approach. This leads to inverse opals or hollow 65 spheres after removal of the template. To prepare inverse opals, usually, a template structure from assembled polymer particles is infiltrated either with a precursor mixture that undergoes a sol-gel 66 67 reaction in the pores or with pre-synthesized TiO₂ nanoparticles. [30] A different approach was used 68 by Lu et al. who first prepared polymer-TiO₂ core-shell particles that were assembled and calcined to 69 get macroporous structures. They were able to prepare phase pure anatase particles at room 70 temperature by using polystyrene particles with grafted poly(styrene sodium sulfonate) chains as 71 template particles. The TiO₂ particles were synthesized by a sol-gel process in between the grafted 72 polymer chains by slowly adding a precursor solution. The core-shell particles were assembled by 73 drying the dispersion and calcined in argon to remain the three-dimensional structure. [4] This 74 synthesis is located between an inverse opal and a hollow sphere synthesis. Hollow sphere objects 75 have evolved over the past years as a particularly interesting shape, owing to the material structuring 76 on multiple length scales: shell, particle diameter, and particle ensemble. [31-33] The particles have a 77 low density but are large enough to be easily filtered and recycled after a catalysis process. 78 Furthermore, the surface area is large and freely accessible from both sides which may be interesting 79 for solar cells or battery devices.

80 A wide-spread and general approach towards hollow sphere structures is based on shell growth on top

of polymeric seed particles. Three steps need to be controlled for this process: 1) Template particle

formation, 2) Shell growth, and 3) Template removal (see Fig. 1).



83

Fig. 1 Overview on the three steps that are needed to prepare TiO2 hollow spheres. First, cationic
polystyrene particles are synthesized via dispersion polymerization, using Polyvinylpyrrolidone (PVP)
as stabilizer, and 2-Methacryloxyethyltrimethylammoniumchloride (MTC) as comonomer. The TiO2
shells are fabricated by a condensation reaction of titanium butoxide (TBT). After an aging step of 24 h
the particles were calcined at 400 °C in air.

89 We briefly outline these steps:

1) The template particles are typically synthesized via emulsifier-free emulsion polymerization or
 dispersion polymerization. The mechanism of dispersion polymerization has been discussed by Barrett

and Arshady and is well known. [34,35] Generally, size control in dispersion polymerization is achieved
by the amount of monomer[36], solvent, [35,37,38], and stabilizer selection, [34,37,38], respectively.
Cheng et al. [36] used an ethanol/water mixture as solvent and polyvinylpyrrolidone (PVP) as stabilizer.
Furthermore, a co-monomer can be used to introduce a specific surface charge.

96 2) Shell growth: One major issue of the TiO_2 shell growth – in contrast to a silica coating – is the high 97 reactivity of the TiO₂ precursors. Barlier et al. examined the condensation reaction in detail. [39] The reaction happens in two steps: the hydrolysis of the titanium precursor and the condensation to the 98 99 TiO_2 network (Scheme 1). Imhof was the first who coated polystyrene (PS) particles with a thin TiO_2 100 layer in a one-step sol-gel approach. [40] Up to now, several more methods have been published based 101 on sol-gel synthesis: varying precursors, solvents, and template particles. [36,41-43] Wang et al. 102 controlled the diffusion of the TiO₂ precursor by synthesizing in an ethanol/acetonitrile mixture. With 103 this approach, they were able to get defined shell thicknesses between 8 – 65 nm on 300 nm anionic 104 PS particles. [43] Taniguchi et al. used grafted poly[2-(N,N-dimethylamino)ethyl]methacrylate chains 105 on PS template particles that catalyzed the hydrolysis and condensation of the TiO₂ precursor and were 106 able to coat template particles in a size range of 90 – 450 nm. [42] Cheng et al. were the only ones who 107 controlled the reaction speed by adding the TiO_2 precursor dropwise within 30 min instead of one 108 quick addition step. Similar to Imhof et al., they used cationic PS template particles that attracted the 109 TiO₂ precursor and lead to shell growth. [36]

- 110
- 111
- 112
- 113
- 114 Scheme 1 Condensation reaction of titanium butoxide in water



115 116

3) There are two options to remove the template particles: dissolution and calcination. Toluene [40]
or THF [41] are commonly used to dissolve non-crosslinked polymer cores via repeated centrifugation
and redispersion. This requires a certain degree of porosity and pore sizes in the coated shell to allow

120 for sufficient mass transport. Cheng et al. removed the core directly after the synthesis while heating 121 the core-shell particles in an ethanol-ammonia mixture. [36] Calcination, however, is the more 122 widespread strategy to remove the template. [41,40,42-44] An inherent side-effect of the thermal 123 decomposition is the concomitant phase transition of the amorphous TiO₂ shell into its anatase form. 124 Therefore, the selection of the right temperature profile and calcination atmosphere is of main 125 importance for the stability of the final hollow particles. It is common to simply heat the samples in air 126 between 500 and 600 °C, followed by an isothermal step of 2 to 3 hrs. [40,42,43] Lu et al. found that 127 their structures collapsed when using this simple approach. That is why they first pyrolised their structures in an inert atmosphere at 500 °C, followed by a calcination step in air to remove the carbon 128 129 that stabilized the structure. [4] Schroden et al. solved the stability problem by applying a more 130 complex heating ramp. Generally, they used very slow heating rates of 2 K/min and heated the sample 131 first to 300 °C for 2 hrs, followed by a second heating step to 400 °C for 2 hrs. With this profile, they 132 were able to get stable inverse opal structures without using an inert atmosphere during the thermal 133 treatment. [25]

134 We build upon these existing methods and provide an approach towards highly uniform TiO_2 hollow 135 spheres with a scalable and simple synthesis route. We used dispersion polymerization to prepare 136 monodisperse polystyrene particles in a size range of 700 nm to 1.3 μ m. Our method extends the range 137 of accessible particle sizes known from emulsifier-free emulsion polymerization considerably, where 138 an upper limit of 600 – 800 nm is known. [45] Furthermore, few purification steps are needed in our 139 protocol, which improves the efficiency and yield of the synthesis. Using a combined mass loss -140 differential scanning calorimetry – infrared analysis, we also provide a better understanding of the 141 calcination mechanism.

142

143 MATERIALS AND METHODS

Materials. 2-Methacryloxyethyltrimethylammoniumchloride (MTC, Sigma-Aldrich GmbH, 75 % soln. in
water), Ethanol abs. (Sigma-Aldrich GmbH, ≥ 99.8 %), Polyvinylpyrrolidone (PVP, Sigma-Aldrich GmbH,
40 000 g/mol), Styrene (Sigma-Aldrich GmbH, > 99 %), Titanium butoxide (TBT, Sigma Aldrich GmbH,
97 %) were used as received. Millipore water was taken from a Millipore Direct Q3UV unit (Merck
Millipore). 2,2'-Azobis(2-methylpropionitril) (AIBN, Sigma-Aldrich GmbH) was recrystallized from
ethanol before use.

Synthesis of PS particles. 3 g PVP (40 000 g/mol) were dissolved in 10 mL ethanol via ultrasonication.
The PVP solution, 46 mL of ethanol, 10 mL ultrapure water, half of the styrene (see table 1), and 300 mg
AIBN were added to a 250 mL three-necked flask equipped with a reflux condenser and a gas inlet. The

153 solution was degassed while stirring with an egg-shaped stirring bar with a speed of 150 rpm. After 154 30 min the mixture was slowly heated to the reaction temperature of 70 °C by turning the hot plate on. 56 mL ethanol, the second half of the styrene, and the MTC were premixed in an Erlenmeyer flask 155 156 and added after 90 min. The reaction was carried out overnight stirring continuously with a speed of 157 150 rpm under a slight argon flow. The polymerization was stopped by exposing the dispersion to 158 ambient air and filtrated using a 125 µm nylon filter sieve. The concentration of the particles was 159 determined gravimetrically. For the calculation of the conversion of the particles, the concentration 160 was divided by the theoretical concentration at 100 % conversion.

161 Synthesis of TiO₂ shells. The synthesis was performed at room temperature. 6.3 mL PS dispersion and 162 37 mL ethanol were added to an Erlenmeyer flask equipped with a septum. The dispersion was stirred 163 at 350 rpm using a magnetic stirrer bar during the degassing and TBT addition steps. The dispersion 164 was degassed for 10 min with argon. 0.8 mL TBT was mixed with 3.2 mL ethanol and added within 165 30 minutes using a syringe pump. After the addition, the dispersion was allowed to age for 24 h 166 without stirring. This aging step is essential to obtain core-shell particles of sufficient mechanical 167 robustness to allow for the final calcination procedure. Particles were washed three times with ethanol 168 for purification.

Synthesis of hollow TiO₂ particles. The particles were freeze-dried in an 80:20 vol% ethanol-water mixture. The PS core was removed by calcination in air. A modified temperature profile of Schroden et al. [25] was used. The samples were heated to 300 °C with a heating rate of 2 K/min, followed by an isothermal step of 2 h. The samples were then heated to 400 °C with a heating rate of 2 K/min, followed by an isothermal step of 12 h. Finally, the sample was cooled down to room temperature for 5 h.

Characterization Methods. Scanning electron microscopy (SEM) and scanning transmission electron
 microscopy (STEM) were performed using a Zeiss Ultraplus instrument using acceleration voltages of
 3 kV or 10 kV. An InLens, Everhard-Thornley, and STEM detector were used. Core-shell particles were
 calcined directly on a silicon wafer or SiO₂ TEM grid (Plano GmbH).

179 The diameter of the PS template particles was evaluated using the MATLAB circle detection function180 (see S1). The search parameters were optimized manually.

Zeta potential was measured using Zetasizer Nano-ZS (Malvern Panalytical). Three measurements
 consisting of 10 – 100 runs were performed. The particles were diluted in ethanol without further
 purification. No additional substances were added to adjust the pH and background salt concentration.
 Transmission electron microscopy (TEM) measurements were performed with a JEOL JEM-2200FS field

185 emission energy filtering transmission electron microscope (FE-EFTEM) operated at an acceleration

voltage of 200 kV. Zero-loss filtered micrographs ($\Delta E \sim 0 \text{ eV}$) were recorded with a bottom-mounted CMOS camera system (OneView, Gatan) and processed with DM 3.3 image processing software (Gatan). Tilt series and tomography reconstructions were performed with SerialEM and IMOD software packages, supporting the entire tomography workflow, from data acquisition to image processing and modeling, developed by David Mastronarde at the Boulder Laboratory for 3D Electron Microscopy (Boulder, Colorado, USA). Videos of the tilt-series of hollow TiO₂ particles were exported from ImageJ distribution Fiji [46].

193 Small-angle X-ray scattering (SAXS) measurements were performed on freeze-dried samples in 1 mm 194 glass capillaries (Hilgenberg, code 4007610, Germany) at room temperature. The measurements were 195 performed in a transmission geometry using a Double Ganesha AIR system (SAXSLAB). A rotating 196 copper anode (MicroMax 007HF, Rigaku Corporation) is the X-ray source of this system. Data was 197 recorded using a position-sensitive detector (PILATUS 300 K, Dectris). Different detector positions were 198 used to cover scattering vectors q between 0.0024 and 0.2 nm⁻¹. The radially averaged data were 199 normalized to the incident beam and sample thickness. Calculations were done using the software 200 SASFIT (version 0.94.1, Kohlbrecher and Bressler) [47] or SasView (version 4.2) [48] or Scatter (version 201 2.5) [49].

202 X-ray powder diffraction patterns for the core-shell and hollow spheres were recorded in Bragg-203 Brentano-geometry on an Empyrean diffractometer (PANalytical B.V.; the Netherlands) using Cu K_{α} 204 radiation (λ = 1.54187 Å).

205 Simultaneous thermal analysis (STA) measurements were performed on a STA 449 F3 Jupiter (Netzsch) 206 equipped with a Bruker Alpha III IR spectrometer using the same temperature ramp that was used for 207 calcination. A DSC/TG OctoS sample holder and PtRh20 crucibles with lids were used. An airflow of 50 208 mL/min was adjusted for the measurement. Differential scanning calorimetry (DSC) measurements show an increase in the baseline at the heating step from 400 to 700 °C, which is caused by the baseline 209 210 calibration. IR measurements were divided by a reference measurement that was taken before the 211 sample measurement started. Due to fluctuations of the baseline over the measurement time, this led 212 to transmission values above 100 % for water bands (3750 cm^{-1} and 1500 cm^{-1}) and CO₂ bands 213 (2250 cm⁻¹). Furthermore, a rubber band baseline correction was performed to cancel out an overall 214 intensity shift that was caused by the increasing temperature of the measured gas.

215

216 RESULTS AND DISCUSSION

217 Synthesis of polystyrene template particles

An overview on the explicit particle recipes is shown in table 1. To control the particlesize, the amount of styrene was increased from 6 mL to 22 mL. As can be seen in Fig. 2a, the particle diameter can be adjusted linearly with the amount of added styrene. The amount of initiator 2,2'-Azobis(2methylpropionitril) (AIBN) does not influence the final particle size. This can be inferred from particles A-E with 0.3 g of AIBN, and particles F-J with 0.15 g AIBN. Further, we find no influence of the initiator concentration on the conversion of the synthesis within this range. The overall conversion was determined to be 80 % to 90 % for all syntheses.

225 Electrostatic stabilization is introduced by the addition of the comonomer 2-226 Methacryloxyethyltrimethylammoniumchloride (MTC). This introduces a positive charge to the 227 particle surface. For particles A-J, we kept the molar ratio between monomer and comonomer 228 constant with a ratio of 0.8 mol-%. This ratio results in a zeta potential of about + 40 mV for all particles. 229 A ratio between monomer and comonomer in the range of 0.8 mol % (particles A-J) up to 1.2 mol % 230 (particles Y) will lead to well-functionalized, stable colloids. This is demonstrated by the synthesis of 231 particles X-Z with different amounts of MTC, while styrene and AIBN concentration were kept constant 232 (Fig. 3). Particles X were fabricated without MTC, resulting in a zeta potential ~ 0 mV. Nevertheless, 233 owing to the use of PVP as a steric stabilizer, the dispersion is still stable. Without MTC, the particles 234 exhibit a very smooth surface. Increasing the amount of MTC to 170 µl lead to a rougher surface, while 235 the particle shape remained spherical. Further increasing the amount of MTC to $300\,\mu l$ lead to 236 aggregated and deformed particles. The particle aggregation is accompanied by a reduction in the 237 overall conversion. The particle diameter decreased by 200 nm from particles X to Y. A potential reason 238 for this deviation from the expected particle diameter is the better solubility of the PS oligomers due 239 to the copolymerization with MTC. This can reduce the tendency for newly formed oligomers to 240 precipitate onto the existing nuclei. As a consequence, the particle growth is less compared to the co-241 monomer free synthesis. Furthermore, newly formed, small nuclei may aggregate on larger particles, 242 resulting in an increasing particle roughness. Overall, using dispersion polymerization it is possible to prepare polymer particles with standard deviations that are less or equal 5 % of the diameter and are, 243 244 therefore, highly monodisperse (see SI Fig. 2). It provides access to a complementary size range with 245 particle sizes around 1 μ m. We want to stress the simplicity of these recipes, where all chemicals, 246 except for AIBN were used without any additional purification.

247

Table 1: Amount of styrene, comonomer 2-Methacryloxyethyltrimethylammoniumchloride, and initiator 2,2'-Azobis(2-methylpropionitril) (AIBN), that was used for the dispersion polymerization with 112 mL ethanol and 10 mL water. Concentration^a, Conversion^a, diameter^b, d, standard deviation^b, σ , and zeta potential, ξ , of the resulting particles.

	V	V	m	Conc.	Conv.	d	σ	٤
Sample	(Styrene)	(MTC)	(AIBN)			(SEM)		
	[mL]	[µL]	[g]	[mg/mL] ^a	[%]ª	[nm] ^b	[%] ^b	[mV] ^d
А	6	109	0.3	65	90	673	1.9	34
В	10	180	0.3	90	87	952	2.4	40
С	14	254	0.3	110	83	1059	3.6	34
D	18	327	0.3	134	82	1196	2.3	39
E	22	400	0.3	158	81	1353	2.8	36
F	6	109	0.15	65	87	735	3.6	378
G	10	180	0.15	89	88	902	5.0	37
н	14	254	0.15	106	80	970	4.2	39
I	18	327	0.15	131	81	1191	2.5	37
J	22	400	0.15	178	92	1374	1.7	38
х	6	0	0.3	65	92	802	2.3	1
Y	6	170	0.3	62	86	621	3.6	34
Z ^c	6	300	0.3	51	69			34

^a determined gravimetrically, ^b measured by SEM image analysis of at least 100 particles, ^c no values
 are provided for diameter and standard deviation, because of an unspherical shape and clustering of
 the particles. ^d the Zeta potential was determined in an ethanolic dispersion

255





260

261 Synthesis of TiO₂ shells

The PS particles were used as seed templates without purification – not even centrifugation after the dispersion polymerization was employed. This procedure is similar to the scalable synthesis of PS@SiO₂ core-shell and SiO₂ hollow spheres, [50], which provided access to gram-scale amounts of hollow silica spheres. An ethanolic solution (V = 4 mL) of the precursor titanium butoxide (TBT) was added with a concentration of 0.6 molL⁻¹ to the ethanolic particle dispersion using a syringe pump within 30 min.

267 We first investigated the influence of the template particle surface functionalization on the TiO_2 268 immobilization and shell formation.



269

Fig. 3 SEM and TEM images of particles X-Z, the corresponding PS@TiO₂ core-shell particles, and hollow
 TiO₂ particles, as well as TEM tomography reconstructions of parts of a slice of the hollow particles

272 Fig. 3 demonstrates the necessity to adjust the cationic surface functionalization. Without the addition 273 of MTC granular TiO₂ nuclei are immobilized on the polymer surface. For both cases of added MTC 274 (particles Y and Z, respectively) an increasingly smooth shell was observed. The granular appearance 275 of the TiO₂ shell is already apparent in the amorphous shell directly after the TiO2 condensation. This 276 can be inferred from the SEM images of the core-shell structures (Fig. 3, second column), where white 277 speckles cover the previously smooth surface. The presence of MTC at the particle surface apparently 278 influences the nucleation and growth mechanism, which we assign to the altered electrostatic 279 environment. Removing the template core by calcination preserves this granularity, which is shown in 280 TEM and TEM tomography images (Fig. 3 right panels). The spherical shape of the hollow sphere is also 281 preserved, which is apparent from the TEM tilt series (see SI gif files). The highest amount of MTC resulted in the most compact and least granular shells. Nevertheless, the TiO_2 coated structures were clustered due to the already clustered particles in the PS seed dispersion. Consequently, a balanced adjustment of the particle surface functionality via MTC is crucial for the colloidal stability and successful coating step.

286 Calcination process

287 Calcination is the final step to obtain hollow TiO₂ particles (Fig. 3 right panel). We want to stress that 288 the core-shell particles can only be transformed into hollow spheres successfully after aging the core-289 shell dispersion for 24 h prior to purification. This aging process apparently improves the formation of 290 a pre-condensed TiO₂ network and proper covalent connectivity among the granular nuclei in the shell. 291 The shell resilience to the thermal decomposition process is improved. Furthermore, the calcination 292 process itself is very important. We used an adapted temperature profile of Schroden et al., [25], 293 where the template removal is achieved in a two-step process. The first calcination step is undertaken 294 just at the onset of PS decomposition at a relatively low temperature (300 °C). The complete 295 degradation of the PS is then achieved by a second step at 400 °C. To gain a deeper understanding of 296 the calcination process, combined TGA, DSC, and IR measurements have been performed in air and 297 nitrogen (see Fig. 4 a-d and Fig. S4).

298 The pure template particles (polystyrene) show three prominent steps. These are directly related to 299 the applied temperature profile. The degradation starts at the end of the first heating ramp (2 K/min) 300 (1). Already 80 % of polystyrene decompose in the form of CO₂ during the isothermal conditions 301 (300 °C), which took 2 h. The PS decomposition is strongly accelerated during the second heat ramp (2 K/min) to 400 °C (2). Within 300 mins another 13 % of PS are decomposed to CO_2 , whereas the 302 303 residues remain by and large stable in air for the 5 h isothermal heating step at 400 °C. The last 5 % of 304 material is fully decomposed during the last heating ramp up to 700 °C (3). The IR spectra (Fig. 4c) only 305 indicated CO_2 as the decomposition product. Single IR spectra of the three steps can be found in the 306 supporting information. Each of the decomposition steps was accompanied by an exothermal event in 307 the DSC signal. This indicates the oxidative decomposition of the polystyrene backbone.[51,52]

The calcination of the core-shell particles shows a couple of interesting deviations from the pure PS decomposition. The degradation starts at the same time/temperature as the pure polystyrene particles (1). Since the IR spectra show exclusively CO_2 bands (see Fig. 4d), it is reasonable to assume that only the polymer decomposed at this point. The PS decomposition, however, is significantly slower compared to the neat seed particles. This could be caused by the limited mass transport to the PS core owing to the presence of the TiO₂ shell. Only 40 % mass has been lost by the end of the first isothermal annealing step at 300 °C. The DSC signal reveals a second event occurring during the isothermal part 315 at 300 °C (2). Xie et al. saw a similar exothermic peak in their differential thermal analysis measurements on TiO₂ particles from different phases at 280 °C. [53] They found that this peak is due 316 317 to the loss of water absorbed at the TiO_2 particle surface. Therefore, the peak can be linked to a 318 precondensation process in the TiO₂ shell and the release of the enclosed water molecules. Owing to the law amount of released water we cannot unambiguously determine the onset of water loss in the 319 IR spectra. The second heating ramp lead to a third prominent step at 400 °C (3). In this case, the 320 degradation product is also CO₂. In contrast to the pure PS particles the last heating step to 700 °C 321 322 results in a very small mass loss of only 2 %. Since the corresponding IR data show no trace of CO₂, all PS must already be decomposed at the end of the second isothermal step and a further condensation 323 324 reaction of the TiO₂ is assumed. Calculations show that 34 % material should be left over, which agrees well with the experimental data of 33 %. We conclude that the TiO₂ shell aids the decomposition 325 326 reaction of the polymer even though the mass transfer is reduced. In our case it is not possible to see the transformation of the amorphous to the anatase phase in the DSC curves. Xi et al. and Li et al. saw 327 328 this event happening at temperatures above 400 °C. [53,54] Therefore, the effect is likely to be 329 superimposed by the exothermic degradation peak of PS.



Fig. 4 Combined STA (a), DSC (b) and IR measurements to investigate the calcination process of pure PS particles (c) and PS@TiO₂ particles (d). Results of SAXS measurements of PS, PS@TiO₂ and TiO₂ hollow spheres (e) and XRD measurements of the PS@TiO₂ and hollow TiO₂ spheres (f). For all measurements, particles Y have been used.

335

336 These results show the importance of the right temperature profile for the calcination process. Since 337 the polymer starts to decompose before the condensation of the TiO_2 takes place, the template particle shrinks, which leads to a shrinkage of the final hollow sphere. The overall particle shrinkage 338 339 can be estimated by the mass loss of the PS particle before the TiO₂ condensation process starts. The 340 mass loss translates into a volume shrinkage of the template particle. Assuming an isotropic shrinkage 341 of the template particle, the diameter of the shrunk particle can be recalculated. The shrunk particle 342 size should then correspond to the final hollow core diameter. Starting with an initial particle with a 343 diameter of 621 nm and considering a mass loss of 40 %, this would result in a shrunk particle diameter 344 of 520 nm. Starting with a PS core diameter of 621 nm and a mass loss of 40 % (Step 2) this would 345 result in a hollow core diameter of 520 nm. This is in reasonable agreement with the experimental data, where the hollow core has a size of ~ 500 nm. Calcinations in inert atmosphere, where the 346 347 template particle is intact much longer, show less shrinkage of the hollow spheres (see SI Fig. 4). 348 Calcination profiles, which omit the mild calcination at 300 °C or that feature too fast heating ramps, 349 sacrifice the shell integrity and result in collapsed structures (see SI Fig. 5).

350 The structure of the polystyrene, core-shell and hollow particles Y (see Fig. 4e), were further 351 characterized by SAXS and SEM/TEM. The measured SAXS data exhibit only week features, which prevent a thorough fitting analysis. Furthermore, PS seed particles are too large to identify the radius 352 353 in the experimentally reachable q range. Thus, based on the TEM result we calculated the form factor 354 of homogeneous spheres with a diameter of 621 nm and compared it to our experimental data – both 355 agree well. The model has a Gaussian size distribution with a standard derivation of 10 %, which is 356 slightly higher compared to the SEM images due to instrumental smearing effects. The measurement 357 of the PS@TiO₂ core-shell particles is shown in Fig. 4e (green symbols). The scattering of PS@SiO₂ can 358 be described by the model of a homogeneous core-homogeneous shell. [50] The sharp and well 359 defined boundary between core and (monodisperse) shell leads to significant oscillations in the 360 scattering data. In contrast to PS@SiO₂ the shell of PS@TiO₂ is less dense and highly particulate (see 361 Fig. 3). As consequence of such a fractal-like shell morphology the corresponding form factor scattering miss such pronounced oscillations. The main features are a q⁻⁴ scaling at intermediate q (ca. 0.008-0.05 362 Å⁻¹) and a q⁻² power law for q > 0.057 Å⁻¹. A very weak oscillation around 0.017 Å⁻¹ hints towards the 363 expected dimension of the shell thickness of about 30-40 nm before calcination. The q⁻² power law for 364 q > 0.057 Å⁻¹ is indicative of strong scatters with a mainly 2D-structure. This is in contrast to scattering 365 patterns of similar (silica-based) core-shell systems [55,56]. These systems exhibit a pronounced form 366 factor and no q⁻² scaling law at high q. The deviation of our system from these findings can be 367 understood by the scattering contrast situation (PS $\approx 9.51 \cdot 10^{-6} \text{ Å}^{-2}$, TiO₂ $\approx 31.8 \cdot 10^{-6} \text{ Å}^{-2}$, no solvent) and 368 369 the lower bending curvature due to the large template particle diameter. At high q the q⁻² term seems to simply add up to the scattering of a pure PS-sphere (q⁻⁴) underlining the fact that the shell is 370

371 particulate. For comparison the scattering of a homogeneous core-homogeneous shell sphere is given 372 (d = 621 nm, 10 % Gaussian distribution and d_{shell} = 35 nm, 20 % Gaussian distribution; green dotted 373 line PS@TiO₂). During the calcination process, the amorphous TiO₂ shells undergo a transformation 374 into anatase phase (Fig. 4f). During this process the overall size of the particle shrinks. The experimental SAXS scattering pattern of this hollow spheres exhibits a minimum at $q \approx 0.026 \text{ Å}^{-1}$. The corresponding 375 376 correlation length of about 24 nm agrees well with the thickness of the TiO₂ shell obtained from TEM analysis. The q^4 behavior at intermediate and high q reflects the contrast situation for a hollow sphere. 377 378 This is corroborated by the calculation of a homogenous hollow sphere (blue dotted line; d_{inner}=621 nm, 10 % Gaussian with zero contrast, $d_{shell} = 24$ nm, 25 % Gaussian with contrast 31.8 $\cdot 10^{-6}$ Å⁻²). The q⁻² 379 380 power law at low q is attributed to the particulate shell, since rough surfaces can be considered as 381 fractals.

As stated above, the TiO₂ shell undergoes a phase transition during the calcination procedure. This can be seen in X-ray diffraction measurements in Fig. 4f. The core-shell particles (green line) do not show any features except for an amorphous halo. This pattern is caused by the TiO₂ and the amorphous polymer core. After calcination, distinct peaks are visible (blue line). The inset shows the normalized data, that agree very well with the expected diffraction pattern of anatase.

387

388 Size series of TiO₂ hollow particles

389 We now want to highlight the robustness of our synthetic protocol. Therefore, TiO₂ shells have been synthesized on PS particles A-E. Setting the MTC/Styrene ratio to 0.8 % during the seed synthesis and 390 the amount of TBT to $5.5 \cdot 10^{-4}$ to $6.5 \cdot 10^{-4}$ mol/m² particle surface during the coating step, it is possible 391 392 to fabricate TiO₂ core-shell particles without secondary nucleation or particle clustering (Fig. 5). When 393 using 800 µl of titanium butoxide, shell thicknesses between 45 nm and 60 nm could be achieved. 394 Stable and smooth TiO₂ shells could be immobilized on the PS seed particles. Also, the template 395 particles themselves remain colloidally stable and are coated as individual objects. One may expect 396 that the shell thickness decreases with increasing template particle diameter when employing the 397 same amount of TBT precursor. This, however, would only be true, if the same particle concentration 398 was used. Owing to our scalable process, we directly use the as-synthesized polymer dispersion, where 399 both, particle diameter and particle concentration vary with the initial monomer concentration. Both 400 parameters cancel each other out leading to comparable shell thicknesses for each batch.

Calcining the particles in air leads to an isotropic shrinkage up to 20 % compared to the core-shell size
(see STEM, Fig. 5). For particles > 700 nm we find no systematic variation of the degree of shrinkage to
the particle size. As a consequence, the TiO₂ hollow spheres B, C, and D all have the same particle

404 diameter of ~ 900 nm; particle E is slightly larger with 1025 nm. Yet, despite the considerable 405 shrinkage, the particles retain their spherical shape and shrink in an isotropic fashion. This is even more 406 remarkable as the ratio t/D between shell thickness (t) and particle diameter (D) is very small. t/D 407 ranges from 4 % for the smallest hollow spheres to 2 % for the largest one. With decreasing t/R ratio 408 the mechanical stability of the TiO₂ hollow spheres decreases, which is also known for their silica shell 409 counterparts [57]. We, consequently, observed an increased portion of fractured or buckled hollow 410 spheres from particles C to E.



411

412 Fig. 5 SEM images of PS@TiO₂ core-shell particles of different sizes (A-E), and corresponding TiO₂
413 hollow spheres. The last row shows STEM images of single TiO₂ hollow spheres.

414

415 CONCLUSIONS

Our contribution addresses several important aspects in the field of templated hollow sphere 416 417 synthesis. We firstly introduced dispersion polymerization as a suitable alternative to established 418 emulsion polymerization techniques for synthesizing template particles in the 500 nm to 1300 nm size 419 regime. The template particles can be functionalized with comonomers to control the particle surface 420 charge. These template beads can be used without additional purification steps for the synthesis of 421 homogeneous TiO₂ shells. This strategy allows for a scalable synthesis of well-coated TiO₂ core-shell 422 particles. However, it is important to control the amount of comonomer used during the dispersion 423 polymerization. This affects the stability of the colloidal particles and the granularity of the TiO₂ shell. 424 We thoroughly investigated the calcination procedure yielding the hollow particles. The usage of an

- 425 isothermal step at the onset of polystyrene decomposition is crucial for retaining the hollow particle
- 426 shape. Our presented method could be applied to a range of template particles with different sizes.
- 427 Overall, this facile, reproducible and scalable method creates well-defined TiO₂ core-shell or hollow
- 428 particles that can be used in applications, where the properties of TiO_2 are beneficial.
- 429

430 ACKNOWLEDGEMENDS

- 431 We thank Stefan Rettinger for the help with STA experiments and the Bavarian Polymer Institute,
- 432 especially Martina Heider, for helping with SEM and STEM measurements. This project was funded by
- 433 the German Research Foundation (DFG RE3550/2-1). Additional support was provided by ERC Starting
- 434 Grant VISIRday under Grant No. 714968. This work benefited from the use of the SasView application,
- 435 originally developed under NSF Award DMR-0520547. SasView also contains code developed with
- 436 funding from EU Horizon 2020 programme under the SINE2020 project Grant No. 654000.
- 437
- 438 CONFLICT OF INTEREST
- 439 The authors declare no conflict of interest.
- 440
- 441 REFERENCES
- 442 1. Anastas P, Eghbali N (2010) Green Chemistry: Principles and Practice. Chem Soc Rev 39 (1):301-312.
 443 doi:10.1039/B918763B
- 444 2. Sheldon RA, Arends I, Hanefeld U (2007) Green Chemistry and Catalysis. Wiley. 445 doi:10.1002/9783527611003
- 446 3. Anastas PT (2007) Introduction: Green Chemistry. Chem Rev 107 (6):2167-2168. 447 doi:10.1021/cr0783784
- 448 4. Lu Y, Hoffmann M, Yelamanchili RS, Terrenoire A, Schrinner M, Drechsler M, Möller MW, Breu J,
- 449 Ballauff M (2009) Well-Defined Crystalline TiO2 Nanoparticles Generated and Immobilized on a 450 Colloidal Nanoreactor. Macromol Chem Phys 210 (5):377-386. doi:10.1002/macp.200800608
- 451 5. Kisch H (2015) Semiconductor Photocatalysis: Principles and Applications. Wiley. 452 doi:10.1002/9783527673315
- 453 6. O'Regan B, Grätzel M (1991) A low-cost, high-efficiency solar cell based on dye-sensitized colloidal
 454 TiO2 films. Nature 353 (6346):737-740. doi:10.1038/353737a0
- 7. Varghese OK, Paulose M, Grimes CA (2009) Long vertically aligned titania nanotubes on transparent
 conducting oxide for highly efficient solar cells. Nature Nanotech 4 (9):592.
 doi:10.1038/nnano.2009.226
- 458 8. Phani G, Tulloch G, Vittorio D, Skryabin I (2001) Titania solar cells: new photovoltaic technology.
 459 Renewable Energy 22 (1):303-309. doi:10.1016/S0960-1481(00)00059-8
- 460 9. Fu LJ, Zhang T, Cao Q, Zhang HP, Wu YP (2007) Preparation and characterization of three-
- 461 dimensionally ordered mesoporous titania microparticles as anode material for lithium ion battery.
 462 Electrochem Commun 9 (8):2140-2144. doi:10.1016/j.elecom.2007.06.009
- 10. Ortiz GF, Hanzu I, Djenizian T, Lavela P, Tirado JL, Knauth P (2009) Alternative Li-Ion Battery
 Electrode Based on Self-Organized Titania Nanotubes. Chem Mat 21 (1):63-67.
 doi:10.1021/cm801670u

- 466 11. Kim K-T, Ali G, Chung KY, Yoon CS, Yashiro H, Sun Y-K, Lu J, Amine K, Myung S-T (2014) Anatase
 467 Titania Nanorods as an Intercalation Anode Material for Rechargeable Sodium Batteries. Nano Lett 14
 468 (2):416-422. doi:10.1021/nl402747x
- 469 12. Chen X, Mao SS (2007) Titanium Dioxide Nanomaterials: Synthesis, Properties, Modifications, and
 470 Applications. Chem Rev 107 (7):2891-2959. doi:10.1021/cr0500535
- 471 13. Reyes-Coronado D, Rodriguez-Gattorno G, Espinosa-Pesqueira ME, Cab C, de Coss R, Oskam G
 472 (2008) Phase-pure TiO(2) nanoparticles: anatase, brookite and rutile. Nanotech 19 (14):145605.
 473 doi:10.1088/0957-4484/19/14/145605
- 474 14. Zaban A, Aruna ST, Tirosh S, Gregg BA, Mastai Y (2000) The Effect of the Preparation Condition of
 475 TiO2 Colloids on Their Surface Structures. J Phys Chem B 104 (17):4130-4133. doi:10.1021/jp993198m
 476 15. Banfield JF, Bischoff BL, Anderson MA (1993) TiO2 accessory minerals: coarsening, and
- 477 transformation kinetics in pure and doped synthetic nanocrystalline materials. Chem Geol 110 (1):211478 231. doi:10.1016/0009-2541(93)90255-H
- 479 16. Yanagisawa K, Ovenstone J (1999) Crystallization of Anatase from Amorphous Titania Using the
 480 Hydrothermal Technique: Effects of Starting Material and Temperature. J Phys Chem B 103 (37):7781481 7787. doi:10.1021/jp990521c
- 482 17. Yin H, Wada Y, Kitamura T, Kambe S, Murasawa S, Mori H, Sakata T, Yanagida S (2001) Hydrothermal
- synthesis of nanosized anatase and rutile TiO2 using amorphous phase TiO2. J Mater Chem 11
 (6):1694-1703. doi:10.1039/B008974P
- 18. Shankar K, Bandara J, Paulose M, Wietasch H, Varghese OK, Mor GK, LaTempa TJ, Thelakkat M,
 Grimes CA (2008) Highly Efficient Solar Cells using TiO2 Nanotube Arrays Sensitized with a DonorAntenna Dye. Nano Lett 8 (6):1654-1659. doi:10.1021/nl080421v
- 488 19. Paulose M, Shankar K, Varghese OK, Mor GK, Hardin B, Grimes CA (2006) Backside illuminated dye489 sensitized solar cells based on titania nanotube array electrodes. Nanotech 17 (5):1446-1448.
 490 doi:10.1088/0957-4484/17/5/046
- 20. Zukalová M, Zukal A, Kavan L, Nazeeruddin MK, Liska P, Grätzel M (2005) Organized Mesoporous
 TiO2 Films Exhibiting Greatly Enhanced Performance in Dye-Sensitized Solar Cells. Nano Lett 5
 (9):1789-1792. doi:10.1021/nl051401l
- 494 21. Somani PR, Dionigi C, Murgia M, Palles D, Nozar P, Ruani G (2005) Solid-state dye PV cells using
 495 inverse opal TiO2 films. Solar Energy Materials and Solar Cells 87 (1):513-519.
 496 doi:10.1016/j.solmat.2004.07.037
- 497 22. Adachi M, Murata Y, Okada I, Yoshikawa S (2003) Formation of Titania Nanotubes and Applications
 498 for Dye-Sensitized Solar Cells. J Electrochem Soc 150 (8):G488-G493. doi:10.1149/1.1589763
- 23. Ohsaki Y, Masaki N, Kitamura T, Wada Y, Okamoto T, Sekino T, Niihara K, Yanagida S (2005) Dyesensitized TiO2 nanotube solar cells: fabrication and electronic characterization. PCCP 7 (24):41574163. doi:10.1039/B511016E
- 502 24. Lim SH, Luo J, Zhong Z, Ji W, Lin J (2005) Room-Temperature Hydrogen Uptake by TiO2 Nanotubes.
 503 Inorg Chem 44 (12):4124-4126. doi:10.1021/ic0501723
- Schroden RC, Al-Daous M, Blanford CF, Stein A (2002) Optical Properties of Inverse Opal Photonic
 Crystals. Chem Mat 14 (8):3305-3315. doi:10.1021/cm020100z
- 26. Retsch M, Jonas U (2013) Hierarchically Structured, Double-Periodic Inverse Composite Opals. Adv
 Funct Mater 23 (43):5381-5389. doi:10.1002/adfm.201300803
- 508 27. Stein A, Wilson BE, Rudisill SG (2013) Design and functionality of colloidal-crystal-templated
 509 materials--chemical applications of inverse opals. Chem Soc Rev 42 (7):2763-2803.
 510 doi:10.1039/c2cs35317b
- 511 28. Noman MT, Ashraf MA, Ali A (2019) Synthesis and applications of nano-TiO2: a review.
- 512 Environmental Science and Pollution Research 26 (4):3262-3291. doi:10.1007/s11356-018-3884-z
- 513 29. Rabenau A (1985) The Role of Hydrothermal Synthesis in Preparative Chemistry. Angewandte
- 514 Chemie International Edition in English 24 (12):1026-1040. doi:10.1002/anie.198510261
- 515 30. Cho C-Y, Moon JH (2012) Hierarchical Twin-Scale Inverse Opal TiO2 Electrodes for Dye-Sensitized
- 516 Solar Cells. Langmuir 28 (25):9372-9377. doi:10.1021/la3014656

- 517 31. Wang X, Feng J, Bai Y, Zhang Q, Yin Y (2016) Synthesis, Properties, and Applications of Hollow Micro-
- 518 /Nanostructures. Chem Rev 116 (18):10983-11060. doi:10.1021/acs.chemrev.5b00731
- 519 32. Chen M, Ye C, Zhou S, Wu L (2013) Recent Advances in Applications and Performance of Inorganic
- Hollow Spheres in Devices. Adv Mater 25 (37):5343-5351. doi:10.1002/adma.201301911
- 33. Zhou L, Zhuang Z, Zhao H, Lin M, Zhao D, Mai L (2017) Intricate Hollow Structures: Controlled
 Synthesis and Applications in Energy Storage and Conversion. Adv Mater 29 (20):1602914.
 doi:10.1002/adma.201602914
- 524 34. Arshady R (1992) Suspension, emulsion, and dispersion polymerization: A methodological survey.
 525 Colloid Polym Sci 270 (8):717-732. doi:10.1007/bf00776142
- 526 35. Barrett KEJ (1973) Dispersion polymerisation in organic media. Br Polym J 5 (4):259-271. 527 doi:doi:10.1002/pi.4980050403
- 528 36. Cheng X, Chen M, Wu L, Gu G (2006) Novel and Facile Method for the Preparation of 529 Monodispersed Titania Hollow Spheres. Langmuir 22 (8):3858-3863. doi:10.1021/la0534221
- 530 37. Kawaguchi S, Ito K (2005) Advances in Polymer Science. In: Polymer Particles, vol 175. Advances in 531 Polymer Science. pp 299-328. doi:10.1007/b100118
- 532 38. Paine AJ, Luymes W, McNulty J (1990) Dispersion polymerization of styrene in polar solvents. 6.
- 533 Influence of reaction parameters on particle size and molecular weight in poly(N-vinylpyrrolidone)-
- 534 stabilized reactions. Macromolecules 23 (12):3104-3109. doi:10.1021/ma00214a012
- 39. Barlier V, Bounor-Legaré V, Boiteux G, Davenas J, Léonard D (2008) Hydrolysis–condensation
 reactions of titanium alkoxides in thin films: A study of the steric hindrance effect by X-ray
 photoelectron spectroscopy. Appl Surf Sci 254 (17):5408-5412. doi:10.1016/j.apsusc.2008.02.076
- 40. Imhof A (2001) Preparation and Characterization of Titania-Coated Polystyrene Spheres and Hollow
 Titania Shells. Langmuir 17 (12):3579-3585. doi:10.1021/la001604j
- 41. Agrawal M, Pich A, Zafeiropoulos NE, Stamm M (2008) Fabrication of hollow titania microspheres
 with tailored shell thickness. Colloid Polym Sci 286 (5):593-601. doi:10.1007/s00396-007-1833-3
- 42. Taniguchi T, Murakami F, Kasuya M, Kojima T, Kohri M, Saito K, Nakahira T (2013) Preparation of
- titania hollow particles with independently controlled void size and shell thickness by catalytic
 templating core–shell polymer particles. Colloid Polym Sci 291 (1):215-222. doi:10.1007/s00396-0122658-2
- 43. Wang P, Chen D, Tang F-Q (2006) Preparation of Titania-Coated Polystyrene Particles in Mixed
 Solvents by Ammonia Catalysis. Langmuir 22 (10):4832-4835. doi:10.1021/la060112p
- 44. Yelamanchili RS, Lu Y, Lunkenbein T, Miyajima N, Yan L-T, Ballauff M, Breu J (2009) Shaping Colloidal
 Rutile into Thermally Stable and Porous Mesoscopic Titania Balls. Small 5 (11):1326-1333.
 doi:10.1002/smll.200801298
- 45. Ruckdeschel P (2017) Transport Phenomena in Silica Hollow Spheres and Hybrid Materials.
 University of Bayreuth, Bayreuth
- 46. Schindelin J, Arganda-Carreras I, Frise E, Kaynig V, Longair M, Pietzsch T, Preibisch S, Rueden C,
- Saalfeld S, Schmid B, Tinevez J-Y, White DJ, Hartenstein V, Eliceiri K, Tomancak P, Cardona A (2012) Fiji:
 an open-source platform for biological-image analysis. Nature Methods 9 (7):676-682.
 doi:10.1038/nmeth.2019
- 47. Bressler I, Kohlbrecher J, Thunemann AF (2015) SASfit: a tool for small-angle scattering data analysis using a library of analytical expressions. J Appl Crystallogr 48 (5):1587-1598. doi:10.1107/S1600576715016544
- 48. Doucet M, Cho, Jae Hie, Alina, Gervaise, Bakker, Jurrian, Bouwman, Wim, Butler, Paul, Washington,
 Adam (2019) SasView version 4.2.2. Zenodo.
- 562 49. Förster S, Fischer S, Zielske K, Schellbach C, Sztucki M, Lindner P, Perlich J (2011) Calculation of
- 563 scattering-patterns of ordered nano- and mesoscale materials. Adv Colloid Interface Sci 163 (1):53-83.
- 564 doi:10.1016/j.cis.2010.12.003
- 565 50. Ruckdeschel P, Dulle M, Honold T, Förster S, Karg M, Retsch M (2016) Monodisperse hollow silica
- 566 spheres: An in-depth scattering analysis. Nano Research 9 (5):1366-1376. doi:10.1007/s12274-016-567 1032-y

- 568 51. Kannan P, Biernacki JJ, Visco DP, Lambert W (2009) Kinetics of thermal decomposition of 569 expandable polystyrene in different gaseous environments. J Anal Appl Pyrolysis 84 (2):139-144. 570 doi:10.1016/j.jaap.2009.01.003
- 571 52. Malhotra SL, Hesse J, Blanchard L-P (1975) Thermal decomposition of polystyrene. Polymer 16 572 (2):81-93. doi:10.1016/0032-3861(75)90133-0
- 573 53. Xie H, Zhang Q, Xi T, Wang J, Liu Y (2002) Thermal analysis on nanosized TiO2 prepared by 574 hydrolysis. Thermochim Acta 381 (1):45-48. doi:10.1016/S0040-6031(01)00642-6
- 575 54. Li D, Chen S, Wang D, Li Y, Shao W, Long Y, Liu Z, Ringer SP (2010) Thermo-analysis of nanocrystalline
- 576 TiO2 ceramics during the whole sintering process using differential scanning calorimetry. Ceram Int 36
- 577 (2):827-829. doi:10.1016/j.ceramint.2009.10.004
- 578 55. Balmer JA, Mykhaylyk OO, Schmid A, Armes SP, Fairclough JPA, Ryan AJ (2011) Characterization of 579 Polymer-Silica Nanocomposite Particles with Core–Shell Morphologies using Monte Carlo Simulations
- 580 and Small Angle X-ray Scattering. Langmuir 27 (13):8075-8089. doi:10.1021/la201319h
- 581 56. Fielding LA, Mykhaylyk OO, Schmid A, Pontoni D, Armes SP, Fowler PW (2014) Visible Mie Scattering
 582 from Hollow Silica Particles with Particulate Shells. Chem Mat 26 (2):1270-1277.
 583 doi:10.1021/cm4039347
- 584 57. Yin J, Retsch M, Lee J-H, Thomas EL, Boyce MC (2011) Mechanics of Nanoindentation on a
- 585 Monolayer of Colloidal Hollow Nanoparticles. Langmuir 27 (17):10492-10500. doi:10.1021/la2018117

586